

Technical Data Sheet



Style 4599

Petromat[®]

nonwoven paving fabric

Petromat[®] Style 4599 is a nonwoven polypropylene paving fabric. We wish to advise that Petromat[®] 4599 meets the following minimum average roll values (MARV) listed below:

Property	Test Method	Minimum Average Roll Value (English)	Minimum Average Roll Value (Metric)
Unit Weight	ASTM-D-5261	3.6 oz/yd ²	122 g/m ²
Tensile Strength	ASTM-D-4632	90 lbs	0.400 kN
Elongation	ASTM-D-4632	50 %	50 %
Mullen Burst	ASTM-D-3786	180 psi	1240 kPa
Asphalt Retention	ASTM-D-6140	0.20 gal/yd ²	0.90 l/m ²
UV Stability	ASTM-D-4355	70 % at 150 hrs	70 % at 150 hrs

Propex Fabrics Inc. manufactures Petromat[®] 4599 in the USA. The values listed are a result of testing conducted in on-site laboratories in accordance with our quality control procedures (QEP). This information will be supplied to Propex Fabrics Inc.'s original customer of record at the time of fabric shipment.

DATE ISSUED: 03/10/05

Propex Fabrics Inc.
260 The Bluffs
Austell, GA 30168
PH: 770-944-4569
PH: 800.445.7732
FX: 770.944.4584 (Quotes)
FX: 770.944.4678 (Technical)
www.geotextile.com

Exclusion of Liability

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex Fabrics Inc. does not warrant its accuracy or completeness. The only warranty made by Propex Fabrics for its products is set forth in our Certificate of Compliance that accompanies our shipment of the product, or such other written warranty as may be agreed by Propex Fabrics and individual customers. Propex Fabrics specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.