



INDUSTRIAL FABRICS, INC.
Since 1981

HEADQUARTERS
510 O' Neal Lane
Baton Rouge, LA 70819

225-273-9600 (Phone)
225-273-0440 (Fax)
www.ind-fab.com (Web)

PRODUCT DATA SHEET FAB 200W

FAB 200W is manufactured using high tenacity polypropylene yarns that are woven to form a dimensionally stable network, which allows the yarns to maintain their relative position. **FAB 200W** resists ultraviolet deterioration, rotting and biological degradation and is inert to commonly encountered soil chemicals.

PROPERTY	TEST METHOD	MARV ENGLISH	MARV METRIC
Tensile Strength (Grab)	ASTM D-4632	200 lbs	890 N
Elongation	ASTM D-4632	15%	15%
Puncture	ASTM D-4833	90 lbs	400 N
Mullen Burst	ASTM D-3786	400 psi	2756 kPa
Trapezoidal Tear	ASTM D-4533	75 lbs	330 N
UV Resistance (at 500 hrs)	ASTM D-4355	70%	70%
Apparent Opening Size (AOS)*	ASTM D-4751	40 US Std. Sieve	0.425 mm
Permittivity	ASTM D-4491	.05 sec¹	.05 sec¹
Water Flow Rate	ASTM D-4491	5 gpm/ft²	204 l/min/m²
Roll Sizes		12.5' x 432' 15.0' x 360' 17.5' x 309'	3.81 m x 131.7 m 4.57 m x 109.8 m 5.33 m x 94.2 m

*Maximum average roll value.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Industrial Fabrics, Inc. assumes no liability in connection with the use of this information.